

# CS Hyde Company

39655 N IL Route 83  
Lake Villa, IL 60046  
Ph. 847-395-0325 Fax 847-395-0334  
[sales@cshyde.com](mailto:sales@cshyde.com) / [www.cshyde.com](http://www.cshyde.com)



## PRODUCT INFORMATION

### 18-4F-P 4 mil. Polyimide Film

#### Product Description:

This polyimide film has an operating temperature range of -269°C to 400°C. This all polyimide film has an excellent balance of properties over a wide temperature range. Common properties include high electrical resistance, good chemical and solvent resistance. RoHs/Reach Compliant.

#### Common Applications:

Mechanical parts, electronic parts, thermal and electrical insulation, fiber optics cable, insulation blankets and tubing, automotive diaphragm sensors and manifolds, etching and shim stock, flex circuits, seal rings, gaskets, and microfluidics.

**\*Perfect for Aerospace, Electronics, Semiconductor, and Chemical Industries.**

#### **Nominal Values**

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

#### **TYPICAL PROPERTIES**

Total Thickness	4 Mil.	
Tensile Strength	24,000 psi.	ASTM D-882-91
Elongation at Rupture	50%	ASTM D-882-91
Breakdown Strength	3500 volts/mil	ASTM D-149-91
Volume Resistivity	$1.0 \times 10^{15}$ Ohm.cm	ASTM D-257-91
Dielectric Constant (1khz)	3-4	ASTM D-150-92
Dissipation Factor (1khz)	$4.0 \times 10^{-3}$	ASTM D-150-92
Operating Temperature Range	-269°C-400°C	

\*The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.